



ALMATIS

PREMIUM ALUMINA



Americas Regional Product Data

Unground Calcined Aluminas

Almatris Calcined Aluminas are produced to consistently achieve the chemical purity and crystal structure necessary to meet the market needs. These products are made in rotary kilns from Bayer alumina produced in Bayer process refineries. The unground calcined aluminas may be used in some processes in their shipped form but more frequently require grinding in the customer's process.

Normal and Intermediate Soda Products

Product	A 2			A 35			CT 800			A13 LS			
	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical	
Chemical Composition (%)													
Al ₂ O ₃ by difference			99.6			99.7			99.7			99.7	
Na ₂ O		0.35	0.25		0.18	0.13		0.15	0.11		0.25	0.11	
Fe ₂ O ₃		0.035	0.02		0.035	0.02		0.04	0.02		0.035	0.02	
SiO ₂		0.03	0.02		0.03	0.01		0.03	0.01		0.03	0.02	
CaO			0.03		0.06	0.03		0.06	0.03			0.03	
B ₂ O ₃		0.035	0.015		0.03	0.003		0.03	0.003		0.02	0.002	
Physical Properties													
Surface Area BET (m ² /g)		0.7	0.4	0.35	0.7	0.5	0.65	0.85	0.7	6.5	15.0	9	
LOI 300 to 1100°C (%)			0.2										
Green Density ⁽¹⁾ (g/cc)						2.27	2.22	2.34	2.28				
Particle Size													
+100M ⁽²⁾ /0.150mm (%)			0-8			0-8			0-8			0-8	
+200M ⁽²⁾ /0.075mm (%)			40-80			40-80			40-80			40-80	
+325M ⁽²⁾ /0.045mm (%)			70-95			70-95			70-95			70-95	
Packaging													
See Std. Packaging (p2)		1, 2, 3, 4, 6			1, 2, 3, 4, 6			1, 3, 4, 6			1, 3, 4, 6		

(1) By Lab Grind

(2) Tyler Mesh

Think alumina, think Almatris.

RP-AM/RCP/004/R13/0914/MSDS 387



Unground Calcined Aluminas

Low Soda Products

Product	A 3500			A 10			CL 3000			A 14		
	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical
Chemical Composition (%)												
Al ₂ O ₃ by difference			99.8			99.7			99.8			99.8
Na ₂ O		0.10	0.08		0.13	0.08		0.08	0.04		0.05	0.03
Fe ₂ O ₃		0.035	0.02		0.05	0.02		0.04	0.02		0.05	0.01
SiO ₂		0.03	0.01		0.12	0.04		0.04	0.02		0.05	0.02
CaO		0.06	0.02			0.03		0.06	0.03		0.06	0.03
B ₂ O ₃		0.03	0.002		0.22	0.10		0.05	0.02		0.06	0.03
Physical Properties												
Surface Area BET (m ² /g)	0.35	0.60	0.5			0.2	0.60	0.75	0.7	0.45	0.70	0.55
Green Density ⁽¹⁾ (g/cc)			2.27				2.24	2.32	2.27			2.31
Particle Size												
Cilas d50 ⁽¹⁾ (µm)	2.1	3.0	2.3	4.2	5.2	4.8	1.4	2.2	1.7	1.6	2.4	1.9
Packaging												
See Std. Packaging (below)	1, 2, 3, 4, 6			1, 4, 5, 6			4, 5, 6			1, 2, 3, 4, 6		

(1) By Lab grind

Standard Packaging

- 50 lb paper bags - 70 per pallet
- 25 kg paper bags - 40 per pallet
- 2500 lb super sacks - 1 per pallet
- 1 mt super sacks - 1 per pallet
- 2755 lb super sacks - 1 per pallet
- Bulk rail car
- Other options available with upcharge

All data is based upon Almatis standard test methods. All test methods are available upon request.
 The typical properties are based upon the actual averages from production data.
 The Min/Max data represents Almatis standard product specification data for these products.



Contacts for sales, technical information and application assistance

Almatis GmbH
 Lyoner Straße 9
 60528 Frankfurt/Germany

Phone **49 69 957 341 0**
 Fax **49 69 957 341 13**

info@almatis.com
www.almatis.com

Almatis, Inc.
 501 West Park Road
 Leetsdale, PA 15056, USA
 Phone
800 643 8771 (within US)
1 412 630 2800 (outside US)
 Fax
1 412 630 2900

Almatis do Brasil Ltda.
 Avenida Jose de Souza
 Campos, 243
 2° Andar – Cambuí
 13025-320 – Campinas,
 SP – Brasil
 Phone
55 19 3515-1400
 Fax
55 19 3515-1410

MSDS 387